

Cooling process for white cement clinker**Publication number:** CN1142471 (A)**Publication date:** 1997-02-12**Inventor(s):** SHUJI YE [CN]**Applicant(s):** YE SHUJI [CN]**Classification:**

- International: C04B7/47; C04B7/00; (IPC1-7): C04B7/47

- European:

Application number: CN19961005635 19960801**Priority number(s):** CN19961005635 19960801**Abstract of CN 1142471 (A)**

A two-step cooling process for clinker of white cement includes the first-step shower cooling the calcined clinker to 100-130 deg.C while bleaching it and the second-step shower cooling to 20-40 deg.C. Its apparatuses include primary shower cooling-bleaching machine, vibration conveyer, belt conveyer, secondary cooler and lifting machine. This new technology features less environmental pollution, increasing quality and reducing the intensity of labour.

Date supplied from the esp@cenet database — Worldwide